



LWM5BB-210

PERC-Mono-crystalline Silicon Solar Cell





Product Features >

Dimension:	156.75mmx156.75mm±0.25mm, Φ210.0mm±0.25mm
Thickness:	200μm±20μm
Front side:	0.7mm wide sliver busbars,Blue silicon nitride anti-reflection coating
Back side:	1.7mm wide sliver busbars,Aluminum local back-surface field

Product Characteristics

- > High conversion efficiency with PERC+SE technology
- No light-induced degradation
- > Uniform cell performance with stable process control
- > Low breakage rate by using high qualified and stable wafers
- Low mismatch of cell performance during encapsulation
- Excellent power generation performance under low irradiation

Quality Control

- Proper inspection through incoming production, outgoing and packaging
- ➤ Efficiency tested within ± 0.1% accuracy
- > 100% checked for reverse current and visual appearance
- > Reference cell calibrated from Fraunhofer
- > ISO 9001,ISO 14001 and CQC etc certificated





Electric Performance >

Eff(%)	Pmpp(W)	Umpp(V)	Impp(A)	Uoc(V)	Isc(A)
22.50%	5.50	0.583	9.436	0.683	8.871
22.40%	5.47	0.581	9.418	0.682	9.864
22.30%	5.45	0.580	9.404	0.681	9.856
22.20%	5.42	0.577	9.392	0.680	9.845
22.10%	5.40	0.576	9.371	0.679	9.836
22.00%	5.38	0.575	9.364	0.677	9.818
21.90%	5.35	0.572	9.350	0.675	9.795
21.80%	5.33	0.571	9.337	0.675	9.795
21.70%	5.30	0.569	9.323	0.674	9.782
21.60%	5.28	0.567	9.315	0.672	9.770
21.50%	5.25	0.565	9.297	0.671	9.763


[•]Under standard test condition: 1000W/ m², AM 1.5G, 25°C

Temperature Coefficients >

Current Temperature Coefficient	Tkcurrent: +0.04%/K
Voltage Temperature Coefficient	Tkvoltage: -0.31 %/K
Power Temperature Coefficient	Tk _{Power} : -0.41%/K

IV Curve >

Spectral Response (SR) >



LIGHTWAY ENERGY TECHNOLOGY CO.,LIMITED

FAB 1: Huacheng/Huifu Rd, Jintan District, Changzhou, Jiangsu, P.R. China

Medicine Industrial Park, Yuangzhou District, Yichun, Jiangxi, P.R. China

FAB 3: Xicheng Industrial Park, Baotian Rd, Xixiang Town, Shenzhen, P.R. China

Version 2020.02 @2020 Lightway Energy Technology Co., Limited All rights reserved.

[•]Average accuracy of all tests is +/-1.5% rel